NYLON SOLUTIONS

Aegis® MBM Nylon 6 Resin for Extrusion Applications

Description

Aegis® MBM is a terminated, non-delustered, bright medium dye, medium viscosity nylon 6 resin for carpet fiber and synthetic turf extrusion applications.

| Typical Properties | Test Method | Unit | Value |
|---------------------|-------------|------|-----------|
| Parameter | | | |
| Viscosity, FAV | ASTM D-789 | | 61 +/- 3 |
| 96% SAV | | | 2.83 |
| Moisture Content | ASTM D-6869 | % | Max. 0.15 |
| Extractable Content | SOP-702-307 | % | Max. 1.1 |

| General Properties | Test Method | Unit | Value |
|---------------------------|-------------|---------|-----------|
| Parameter | | | |
| Melting Point | ASTM D-3418 | °C (°F) | 220 (428) |
| Density (Typical) | ASTM D-1505 | g/cm³ | 1.13 |
| Forms | | | Pellets |

Processing Guidelines

Material Handling

Aegis® MBM resin is supplied in sealed containers and drying prior to processing is not required. However, high moisture is the primary cause of processing problems. If drying becomes necessary, a dehumidifying or desiccant dryer operating at 80°C (176°F) is recommended. Drying time is dependent on moisture level. Further information concerning safe handling procedures can be obtained from the Safety Data Sheet. Alternatively, please contact your AdvanSix representative.

The values presented in this data sheet are typical values and are not to be interpreted as product specifications.

Contact AdvanSix

To learn more about the benefits of of Aegis® Nylon Resins, visit AdvanSix.com/NylonSolutions or call: 1-844-890-8949 (toll free, U.S./Can.) +1-973-526-1800 (international)

RESPONSIBLE CARE

Although AdvanSix Inc. believes that the information contained herein is accurate and reliable, it is presented without guarantee or responsibility of any kind and does not constitute any representation or warranty of AdvanSix Inc., either expressed or implied. A number of factors may affect the performance of any products used in conjunction with user's materials, such as other raw materials, application, formulation, environmental factors and manufacturing conditions among others, all of which must be taken into account by the user in producing or using the products. The user should not assume that all necessary data for the proper evaluation of these products are contained herein. Information provided herein does not relieve the user from the responsibility of carrying out its own tests and experiments, and the user assumes all risks and liabilities (including, but not limited to, risks relating to results, patent infringement, regulatory compliance and health, safety and environment) related to the use of the products and/or information contained herein.

