

NYLON SOLUTIONS

Capran® HS Red Tinted, Heat-stabilized Blown Nylon 6 Film

Description

Capran® HS Red is a red tinted, heat-stabilized blown film produced from low lactam nylon 6 resin. It is recommended as a bagging film for advanced composite fabrication and other high-temperature applications where softness and workability are essential. Capran® HS Red has excellent heat stability and resistance to pin-holing, and is available in sheet, tube and V-sheet in widths ranging from 48" to 80".

Product Specifications		
Thickness (ASTM D-6988)		Yield (calculated)
Average	Single Point Minimum	
2.00 mils (50.8 microns) ± 12%	1.70 mils (43.2 microns)	12,224 in ² /lb (17.4 m ² /kg) ± 12%
3.00 mils (76.2 microns) ± 12%	2.55 mils (64.8 microns)	8,151 in ² /lb (11.6 m ² /kg) ± 12%

Properties @ 73°F (22.7°C), 50% RH	Typical Values		Test Method
	English	Metric	
Tensile Strength @ Break	14,000 psi	96 MPa	ASTM D-882
Elongation @ Break	415%		ASTM D-882
Modulus, Secant	80,000 psi	552 MPa	ASTM D-882
Melting Temperature (T _m)	424°F	218°C	DSC
Maximum Recommended Use Temperature ¹	400°F	204°C	—

¹The maximum recommended use temperature is a function of the duration at maximum temperature and is process specific.

Capran® HS Red, like all nylon films, is a hydrophilic or water-sensitive material. Moisture and water act as plasticizers. The higher the moisture content of the film, the more flexible it becomes. The lower the plasticizer content, the stiffer it becomes. The level of moisture content at time of use is an important factor for successful performance.

The values presented in this data sheet are typical values and are not to be interpreted as product specifications.

Contact AdvanSix

To learn more about the benefits of Capran® films, visit AdvanSix.com/NylonSolutions or call: **1-844-890-8949** (toll free, U.S./Can.) **+1-973-526-1800** (international)

AdvanSix
300 Kimball Drive, Suite 101
Parsippany, NJ 07054

Although AdvanSix Inc. believes that the information contained herein is accurate and reliable, it is presented without guarantee or responsibility of any kind and does not constitute any representation or warranty of AdvanSix Inc., either expressed or implied. A number of factors may affect the performance of any products used in conjunction with user's materials, such as other raw materials, application, formulation, environmental factors and manufacturing conditions among others, all of which must be taken into account by the user in producing or using the products. The user should not assume that all necessary data for the proper evaluation of these products are contained herein. Information provided herein does not relieve the user from the responsibility of carrying out its own tests and experiments, and the user assumes all risks and liabilities (including, but not limited to, risks relating to results, patent infringement, regulatory compliance and health, safety and environment) related to the use of the products and/or information contained herein.



AdvanSix Caring™

Capran® is a registered trademark of AdvanSix Inc.
May 2018-3, Printed in U.S.A.
©2018 AdvanSix Inc. All rights reserved.