

# Aegis® PIR-H100QP Nylon 6 Extrusion Grade Homopolymer



## Description

**Aegis® PIR-H100QP** resin from AdvanSix contains 100% post-industrial recycled (PIR) raw materials<sup>1</sup> while providing the same top performance and processability as Aegis® H100QP, its standard, non-recycled counterpart.

Aegis® PIR-H100QP is a lubricated, medium viscosity, nylon 6 extrusion grade homopolymer for cast or blown film. It conforms to FDA requirements of 21 CFR 177.1500 as well as EU Directive 2011/10/EC. Aegis® PIR-H100QP homopolymer possesses the combination of strength, toughness and thermoforming properties associated with nylon 6 as well as excellent heat, chemical and abrasion resistance.

Typical Properties	ASTM Test Method	Dry	Conditioned
<b>Parameter</b>			
Viscosity, FAV	D-789	100	-
96% SAV		3.37	-
Melt Flow Rate, 235°C/1.0 kg (455°F/1.0 kg); g/10 min	D-1238	2.6	-
<b>Gas Barrier @ 23°C (73°F)/0% RH</b>			
Oxygen Permeability, cc/m <sup>2</sup> /day (cc/100 in <sup>2</sup> /day)		40.3 (2.600)	-
Nitrogen Permeability, cc/m <sup>2</sup> /day (cc/100 in <sup>2</sup> /day)		14.0 (0.903)	-
Carbon Dioxide Permeability, cc/m <sup>2</sup> /day (cc/100 in <sup>2</sup> /day)		72.8 (4.697)	-
<b>Moisture</b>			
Moisture Content, %		Max. 0.08	-
Extractable Content, %		Max. 0.8	-
Water Absorption in 24 hrs, %		1.6	-
Equilibrium Moisture @ 50% RH, %		2.7	-
Saturation Moisture Content, %		9.5	-
<b>Density, g/cm<sup>3</sup></b>	D-1505	1.13	-
<b>Thermal</b>			
Melting Point	D-3418	220°C (428°F)	-

## Processing Guidelines

### Material Handling

Aegis® PIR-H100QP is supplied in sealed containers and drying prior to processing is not required. However, higher moisture is the primary cause of processing issues. If drying becomes necessary, a dehumidifying or desiccant dryer operating at 80°C (176°F) is recommended. Drying time is dependent on moisture level. More information about safe handling procedures can be obtained by requesting the Safety Data Sheet on [AdvanSix.com](http://AdvanSix.com).

<sup>1</sup>Using an industry-accepted mass balance method, AdvanSix allocates recycled material into 100% PIR Aegis® resins. PIR grades are certified by an independent third-party organization (SCS Global Services) for recycled content, with annual audits.

The values presented in this data sheet are typical values and are not to be interpreted as product specifications.

Although AdvanSix Inc. believes that the information contained herein is accurate and reliable, it is presented without guarantee or responsibility of any kind and does not constitute any representation or warranty of AdvanSix Inc., either expressed or implied. A number of factors may affect the performance of any products used in conjunction with user's materials, such as other raw materials, application, formulation, environmental factors and manufacturing conditions among others, all of which must be taken into account by the user in producing or using the products. The user should not assume that all necessary data for the proper evaluation of these products are contained herein. Information provided herein does not relieve the user from the responsibility of carrying out its own tests and experiments, and the user assumes all risks and liabilities (including, but not limited to, risks relating to results, patent infringement, regulatory compliance and health, safety and environment) related to the use of the products and/or information contained herein.

## Extrusion Guidelines

### Melt Viscosity vs. Temperature

Melt Temperature: 220°C (428°F)

Melt Temperature Range: 232°C (450°F) to 271°C (520°F)

Two key factors affect the melt viscosity (stiffness or fluidity of the melt):

1. The molecular weight (Mw) of the resin: Higher Mw resins will have a higher melt viscosity than lower Mw resins.
2. Temperature of the melt for any given Mw resin: Higher process temperatures will provide a more fluid melt viscosity than lower process temperatures.

### Typical Barrel Profile for Cast Films

Barrel: 230-260°C (446-500°F)

Adapter: 260-266°C (500-510°F)

Die: 260°C (500°F)

Process Melt Temperature: 260-270°C (500-518°F)

### Typical Barrel Profile for Tubular (Blown) Films

Barrel: 246-254°C (474-490°F)

Adapter: 260°C (500°F)

Die: 254°C (490°F)

Process Melt Temperature: 254-260°C (490-500°F)

### Screw Parameters

Metering Section: 40%

Transition Section: 3 to 4 flights

Feed Section: Balance of screw length

Compression Ratio: 3.5:1 to 4.0:1

L/D Ratio: 24:1

### Metering Section Flight Depth

Screw Diameter	Recommended Depth
1"	0.055"
1.5"	0.060"
2"	0.070"
2.5"	0.080"
3.5"	0.100"
4.5"	0.115"
6"	0.135"

Note: The values in this data sheet are for natural color resins only. Colorants or other additives may alter some or all of these properties. The data listed here fall within the normal range of product properties, but should not be used to establish specification limits nor used alone as the basis of design.

*The values presented in this data sheet are typical values and are not to be interpreted as product specifications.*

Page 2 of 3

Although AdvanSix Inc. believes that the information contained herein is accurate and reliable, it is presented without guarantee or responsibility of any kind and does not constitute any representation or warranty of AdvanSix Inc., either expressed or implied. A number of factors may affect the performance of any products used in conjunction with user's materials, such as other raw materials, application, formulation, environmental factors and manufacturing conditions among others, all of which must be taken into account by the user in producing or using the products. The user should not assume that all necessary data for the proper evaluation of these products are contained herein. Information provided herein does not relieve the user from the responsibility of carrying out its own tests and experiments, and the user assumes all risks and liabilities (including, but not limited to, risks relating to results, patent infringement, regulatory compliance and health, safety and environment) related to the use of the products and/or information contained herein.

Aegis® is a registered trademark of AdvanSix Inc.

September 2021-2

©2021 AdvanSix Inc. All rights reserved.



**Contact AdvanSix**

To learn more about the benefits of Aegis® Nylon Resins, visit [AdvanSix.com/NylonSolutions](https://www.advansix.com/NylonSolutions) or call: **1-844-890-8949** (toll free, U.S./Can.) **+1-973-526-1800** (international)

Although AdvanSix Inc. believes that the information contained herein is accurate and reliable, it is presented without guarantee or responsibility of any kind and does not constitute any representation or warranty of AdvanSix Inc., either expressed or implied. A number of factors may affect the performance of any products used in conjunction with user's materials, such as other raw materials, application, formulation, environmental factors and manufacturing conditions among others, all of which must be taken into account by the user in producing or using the products. The user should not assume that all necessary data for the proper evaluation of these products are contained herein. Information provided herein does not relieve the user from the responsibility of carrying out its own tests and experiments, and the user assumes all risks and liabilities (including, but not limited to, risks relating to results, patent infringement, regulatory compliance and health, safety and environment) related to the use of the products and/or information contained herein.

**AdvanSix**  
300 Kimball Drive, Suite 101  
Parsippany, NJ 07054



Aegis® is a registered trademark of AdvanSix Inc.  
September 2021-2  
©2021 AdvanSix Inc. All rights reserved.

