

OxyShield® OMB 1200 Biaxially Oriented Nylon 6 Film

Description

OxyShield® OMB 1200 is a 0.47 mil (12 micron) biaxially oriented nylon 6 film with Corona treatment on the outside of the reel. EVOH is incorporated in the core layer to provide additional barrier to oxygen. OxyShield® OMB 1200 features a superior balance of properties, including high barrier to both oxygen and aromas, excellent toughness and puncture resistance under both high and low temperatures, exceptional flex crack resistance and optics. OxyShield® OMB 1200 is particularly recommended for packaging requiring high oxygen barrier OTR <5 cc/m²/24 hours, such as 'doy pack' for mayonnaises, containers for seafood, dairy products, processed meats and pastas.

Properties		Typical Value		Test Method
		English	Metric	
Average Thickness	Target	0.47 mil	12 micron	AdvanSix Method
Basis Weight		8.56 lbs/ream	14.0 g/m ²	AdvanSix Method
Yield		50,500 sq. in/lb	71.8 m ² /kg	AdvanSix Method
Tensile Strength @ Break	MD	34,800 psi	240 MPa	ASTM D-882
	TD	45,000 psi	310 MPa	
Elongation @ Break	MD	110%		ASTM D-882
	TD	80%		
Elastic Modulus	MD	503,000 psi	3,470 MPa	ASTM D-882
	TD	424,000 psi	2,920 MPa	
Dimensional Stability	MD	1.5%		
	TD	1.5%		
Haze		3.5%		ASTM D-1003
Surface Tension	Treated Side	58 dynes/cm		ASTM D-2578
Coefficient of Friction, Kinetic	In/In	0.40		ASTM D-1894
	Out/Out	0.45		
Oxygen Transmission Rate @ 71.6°F/0% RH, 22°C/0% RH		0.3 cc/100 in ² .day	4.7 cc/m ² .day	ASTM D-3985

The properties presented in this data sheet are typical values and are not to be interpreted as product specifications.

Contact AdvanSix

To learn more about the benefits of OxyShield® films, visit AdvanSix.com or call: **1-844-890-8949** (toll free, U.S./Can.) **+1-973-526-1800** (international)

AdvanSix
300 Kimball Drive, Suite 101
Parsippany, NJ 07054

Although AdvanSix Inc. believes that the information contained herein is accurate and reliable, it is presented without guarantee or responsibility of any kind and does not constitute any representation or warranty of AdvanSix Inc., either expressed or implied. A number of factors may affect the performance of any products used in conjunction with user's materials, such as other raw materials, application, formulation, environmental factors and manufacturing conditions among others, all of which must be taken into account by the user in producing or using the products. The user should not assume that all necessary data for the proper evaluation of these products are contained herein. Information provided herein does not relieve the user from the responsibility of carrying out its own tests and experiments, and the user assumes all risks and liabilities (including, but not limited to, risks relating to results, patent infringement, regulatory compliance and health, safety and environment) related to the use of the products and/or information contained herein.



OxyShield® is a registered trademark of AdvanSix Inc.
May 2020-4, Printed in U.S.A.
©2020 AdvanSix Inc. All rights reserved.