

DESCRIPTION

Aegis® H35ZI is an unfilled, low viscosity, non-lubricated nylon 6 injection molding homopolymer exhibiting excellent melt flow properties for filling thin sections and reduced cycle times. Aegis® H35ZI homopolymer exhibits good strength, stiffness and toughness as well as excellent heat, chemical and abrasion resistance.

TYPICAL PROPERTIES	TEST METHOD	UNIT	VALUE
Parameter			
Viscosity, FAV	ASTM D-789		38 +/- 3
96% SAV			2.39
Moisture Content	ASTM D-6869	%	Max. 0.10
Extractable Content	SOP-702-307	%	Max. 0.8
Physical			
Density	ASTM D-792	g/cm ³	1.12
Mold Shrinkage Linear Flow	ASTM D-955	%	1.27
Rockwell Hardness, R Scale	ASTM D-785		119
Moisture (24 Hour)	ASTM D-570	%	1.6
Moisture (50% RH)	ASTM D-570	%	2.7
Moisture (Saturation)	ASTM D-570	%	9.5
Melt Flow Rate, 235°C/1.0 kg (455°F/1.0 kg)	ASTM D-1238	g/10 min	22.7
Mechanical			
Tensile Modulus, 23°C (73°F)	ASTM D-638	MPa (psi)	2,750 (398,854)
Tensile Strength, Yield, 23°C (73°F)	ASTM D-638	MPa (psi)	79 (11,458)
Elongation, Yield, 23°C (73°F)	ASTM D-638	%	4.1
Elongation, Break, 23°C (73°F)	ASTM D-638	%	75
Flexural Modulus, 23°C (73°F)	ASTM D-790	MPa (psi)	2,465 (357,518)
Flexural Strength, 23°C (73°F)	ASTM D-790	MPa (psi)	96 (13,924)
Impact			
Notched Izod Impact, -40°C (-40°F)	ASTM D-256	J/m (ft-lbs/in)	45
Notched Izod Impact, 23°C (73°F)	ASTM D-256	J/m (ft-lbs/in)	46
Thermal			
Melting Point	ASTM D-3418	°C (°F)	222°C (432°F)
Heat Deflection @ 264 psi (1.8 MPa)	ASTM D-648	°C (°F)	47°C (117°F)
Heat Deflection @ 66 psi (0.45 MPa)	ASTM D-648	°C (°F)	152°C (306°F)
Coef. of Linear Thermal Expansion	ASTM D-831	µm/mm °C	72

PROCESSING GUIDELINES

Material Handling

Aegis® H35ZI homopolymer is supplied in sealed containers and drying prior to processing is not required. However, high moisture is the primary cause of processing problems. If drying becomes necessary, a dehumidifying or desiccant dryer operating at 80°C (176°F) is recommended. Drying time is dependent on moisture level. Further information concerning safe handling procedures can be obtained from the Safety Data Sheet. Alternatively, please contact your AdvanSix representative.

INJECTION MOLDING GUIDELINES

Typical Profile

Melt Temperature: 240–280°C (464–536°F)

Mold Temperature: 80–95°C (176–203°F)

Injection and Packing Pressure: 35–125 bar (500–1500 psi)

Mold Temperatures

A mold temperature of 80–95°C (176–203°F) is recommended, but temperatures as low as 10°C (50°F) can be used where applicable.

Pressures

Injection pressure controls the filling of the part and should not be applied for 90% of ram travel. Packing pressure affects the final part and can be used effectively in controlling sink marks and shrinkage. It should be applied and maintained until the gate area is completely frozen off.

Fill Rate

Fast fill rates are recommended to ensure uniform melt delivery to the cavity and to prevent premature freezing.

NOTE

The values presented in this data sheet are typical values and are not to be interpreted as product specifications.

The values in this data sheet are for natural color resins only. Colorants or other additives may alter some or all of these properties. The data listed here fall within the normal range of product properties, but should not be used to establish specification limits nor used alone as the basis of design.

Although AdvanSix Inc. believes that the information contained herein is accurate and reliable, it is presented without guarantee or responsibility of any kind and does not constitute representation or warranty of AdvanSix Inc., either expressed or implied. A number of factors may affect the performance of products used in conjunction with user's materials, such as other raw materials, application, formulation, environmental factors and manufacturing conditions among others, all of which must be taken into account by the user in producing or using the products. The user should not assume that all necessary data for the proper evaluation of these products are contained herein. Information provided in this document does not relieve the user from the responsibility of carrying out independent tests and experiments, and the user assumes all risks and liabilities (including, but not limited to, risks relating to results, patent infringement, regulatory compliance and health, safety and environment) related to the use of the products and/or information contained herein.

Aegis® is a registered trademark of AdvanSix Inc.
©2024 AdvanSix Inc. All rights reserved.

CONTACT ADVANSIX

Contact AdvanSix to learn more about the benefits of Aegis® Nylon Resins.

ADVANSIX.COM
1-844-890-8949 (TOLL FREE, U.S./CAN.)
+1-973-526-1800 (INTERNATIONAL)

ADVANSIX HEADQUARTERS

300 Kimball Drive, Suite 101
Parsippany, NJ 07054

