

DESCRIPTION

Aegis® MBM is a terminated, non-delustered, bright medium dye, medium viscosity nylon 6 resin for carpet fiber and synthetic turf extrusion applications.

PHYSICAL AND CHEMICAL PROPERTIES

GENERAL PROPERTIES	TEST METHOD	UNIT	VALUE
Parameter			
Viscosity, FAV	ASTM D-789		61 +/- 3
96% SAV			2.83
Moisture			
Moisture Content	ASTM D-6869	%	Max. 0.15
Extractable Content	SOP-702-307	%	Max. 1.1
Density (Typical)	ASTM D-1505	g/cm ³	1.13
Thermal			
Melting Point	ASTM D-3418	°C (°F)	220°C (428°F)
Forms			Pellets

PROCESSING GUIDELINES

Material Handling

Aegis® MBM is supplied in sealed containers and drying prior to processing is not required. However, higher moisture is the primary cause of processing issues. If drying becomes necessary, a dehumidifying or desiccant dryer operating at 80°C (176°F) is recommended. Drying time is dependent on moisture level. More information about safe handling procedures can be obtained by requesting the Safety Data Sheet on AdvanSix.com.

NOTE

The values presented in this data sheet are typical values and are not to be interpreted as product specifications.

The values in this data sheet are for natural color resins only. Colorants or other additives may alter some or all of these properties. The data listed here fall within the normal range of product properties, but should not be used to establish specification limits nor used alone as the basis of design.

Although AdvanSix Inc. believes that the information contained herein is accurate and reliable, it is presented without guarantee or responsibility of any kind and does not constitute any representation or warranty of AdvanSix Inc., either expressed or implied. A number of factors may affect the performance of any products used in conjunction with user's materials, such as other raw materials, application, formulation, environmental factors and manufacturing conditions among others, all of which must be taken into account by the user in producing or using the products. The user should not assume that all necessary data for the proper evaluation of these products are contained herein. Information provided herein does not relieve the user from the responsibility of carrying out its own tests and experiments, and the user assumes all risks and liabilities (including, but not limited to, risks relating to results, patent infringement, regulatory compliance and health, safety and environment) related to the use of the products and/or information contained herein.

Aegis® is a registered trademark of AdvanSix Inc.
©2023 AdvanSix Inc. All rights reserved.

CONTACT ADVANSIX

Contact AdvanSix to learn more about the benefits of our Nylon Resins.

ADVANSIX.COM
1-844-890-8949 (TOLL FREE, U.S./CAN.)
+1-973-526-1800 (INTERNATIONAL)

ADVANSIX HEADQUARTERS

300 Kimball Drive, Suite 101
Parsippany, NJ 07054

